

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.5	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.016	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	680	MPa	ASTM D 638
Tensile Strength at Yield	25	MPa	ASTM D 638
Elongation at Break	350	%	ASTM D 638
Flexural Modulus	680	MPa	ASTM D 790
Flexural Strength	30	MPa	ASTM D 790
Shore D Hardness	62	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	62	°C	ASTM D 648
DTUL @ 264 psi	48	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	910	kg/m ³	ASTM D 792

Characteristics

Processing

Other Extrusion

Delivery form

Black

Features

Copolymer

Applications

Automotive

Regional Availability

North America