

Product Texts

LNP STAT-KON DEL33EC compound is based on Polycarbonate (PC) resin containing 15% carbon fiber, 15% PTFE. Added features of this grade include: LNP Clean Compounding Technology, Electrically Conductive, Wear Resistant, Easy Molding.

UL Yellow Card Link [E207780-101977558](https://www.ul.com/yellow-card/E207780-101977558)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.1	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	0.1	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.5	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	7890	MPa	ISO 527
Stress at break	96	MPa	ISO 527
Strain at break	3.4	%	ISO 527
Flexural modulus	7840	MPa	ISO 178
Flexural strength	160	MPa	ISO 178
Izod impact strength, +23°C, 4mm	33	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	8	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	8480	MPa	ASTM D 638
Tensile Strength at Break	97	MPa	ASTM D 638
Elongation at Break	3.2	%	ASTM D 638
Flexural Modulus	7300	MPa	ASTM D 790
Flexural Strength	159	MPa	ASTM D 790
Izod Impact notched, 1/8 in	84	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	415	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	141	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	146	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	1.0	mm	-
ASTM Data			
DTUL @ 66 psi	145	°C	ASTM D 648
DTUL @ 264 psi	141	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1000000	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Humidity absorption	0.21	%	Sim. to ISO 62
Water Absorption, 24hr	0.15	%	ASTM D 570
Density	1340	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	305 - 325	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	295 - 305	°C	-

LNP™ STAT-KON™ Compound DEL33EC

(PC+PTFE)-CF15

Saudi Basic Industries Corporation (SABIC)

Zone 2	310 - 320	°C	-
Zone 3	320 - 330	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Increased electrical conductivity