

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	7	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.016	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	1200	MPa	ASTM D 638
Tensile Strength at Yield	25	MPa	ASTM D 638
Elongation at Break	50	%	ASTM D 638
Flexural Modulus	1200	MPa	ASTM D 790
Flexural Strength	34	MPa	ASTM D 790
Rockwell Hardness	R 90	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	110	°C	ASTM D 648
DTUL @ 264 psi	58	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	905	kg/m ³	ASTM D 792

Characteristics

Features
Copolymer

Regional Availability
North America

Applications
Automotive