

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.016	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	1500	MPa	ASTM D 638
Tensile Strength at Yield	26	MPa	ASTM D 638
Elongation at Break	125	%	ASTM D 638
Flexural Modulus	1500	MPa	ASTM D 790
Flexural Strength	38	MPa	ASTM D 790

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	100	°C	ASTM D 648
DTUL @ 264 psi	58	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics

Special Characteristics
U.V. stabilized or stable to weather

Applications
Automotive

Features
Copolymer

Regional Availability
North America