

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	22	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.016	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	1000	MPa	ASTM D 638
Tensile Strength at Yield	24	MPa	ASTM D 638
Elongation at Break	135	%	ASTM D 638
Flexural Modulus	1000	MPa	ASTM D 790
Flexural Strength	35	MPa	ASTM D 790
Shore D Hardness	58	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	90	°C	ASTM D 648
DTUL @ 264 psi	55	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Special Characteristics

U.V. stabilized or stable to weather

### Features

Copolymer

### Applications

Automotive

### Regional Availability

North America