

Product Texts

Premium propylene homopolymer produced using ExxonMobil Chemical's Exxpol Technology. The resin is designed for spunbond and fine denier fiber applications.

Excellent uniformity for high-speed spinning of fine denier fibers. Contains stabilizer package suitable for most nonwoven and filament products.

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 24 | g/10min | ASTM D 1238 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 900 | kg/m ³ | ASTM D 792 |

Characteristics**Processing**

Fiber Extrusion, Other Extrusion

Features

Low Smoke, Homopolymer

Delivery form

Pellets, Natural Color

Regional Availability

North America, South and Central America