

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	20	MPa	ASTM D 638
Tensile Strength at Break	22	MPa	ASTM D 638
Elongation at Break	300	%	ASTM D 638
Shore D Hardness	63	-	ASTM D 2240
Izod Impact notched, 1/8 in	700	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	100	J/m	ASTM D 256
Temperature	-20	°C	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Vicat Temperature	146	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Coating

Features

Good Adhesion

Delivery form

Powder

Regional Availability

Europe