

ADMER™ AT3115E

PP

Mitsui Chemicals Europe GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	28	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	26	MPa	ASTM D 638
Elongation at Break	100	%	ASTM D 638
Shore D Hardness	65	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Vicat Temperature	126	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	910	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Applications

Packaging

Delivery form

Pellets

Regional Availability

Europe

Certifications

Food contact, Food approval 10/2011