APLAX® P0070GN 15

PP

Ginar Technology Co.,Ltd.

Product Texts

Application: Ultrafine denier melt blown non-woven fabrics.

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards[S]			
Melt Flow Index, MFI	**1500**	g/10min	GB/T 3682
Temperature	**230**	°C	-
Load	**2.16**	kg	-

S: These properties are reported by the producer according standards that are different to our defaults.

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	**165**	°C	ASTM D 3418

Characteristics

Processing

Blow Molding

Features

Homopolymer

Certifications

RoHS compliant

Regional Availability

Europe, Asia Pacific

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.