

Product Texts

Applications: Ultrafine denier melt blown non-woven fabrics, Typical applications includes diapers, sanitary napkins, oil absorbent mats, wipes, wet tissues, masks, air filtration media and medicals.

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards^[5]			
Melt Flow Index, MFI	1500	g/10min	GB/T 3682
Temperature	230	°C	-
Load	2.16	kg	-

S: These properties are reported by the producer according standards that are different to our defaults.

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	165	°C	ASTM D 3418

Characteristics

Processing

Blow Molding

Chemical Resistance

Oil Resistance

Certifications

Food contact, Food approval FDA 21 CFR, RoHS compliant

Applications

Medical

Regional Availability

Europe, Asia Pacific