

**ARBOFILL® Buche**

PP

TECNARO GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	10	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
<b>Other Standards<sup>[S]</sup></b>			
Molding shrinkage, parallel	1.0	%	Company Standard

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	3000	MPa	ISO 527
Tensile Strength	33	MPa	ISO 527
Stress at break	32	MPa	ISO 527
Strain at break	4.5	%	ISO 527
Charpy impact strength, +23°C	15	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	3	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	104	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
<b>Other Standards<sup>[S]</sup></b>			
Density	1010	kg/m <sup>3</sup>	Company Standard

S: These properties are reported by the producer according standards that are different to our defaults.

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets, Brown

**Certifications**

Contains renewable resources, Food contact, Food approval 1935/2004/EC, Food approval 10/2011

**Regional Availability**

Europe