

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	20	MPa	ISO 527
Strain at break	35	%	ISO 527
Flexural modulus, 23°C	1200	MPa	ISO 178
Izod notched impact strength, +23°C	9	kJ/m ²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	970	kg/m ³	ISO 1183

Characteristics

Processing
Injection Molding

Features
Copolymer

Delivery form
Black

Certifications
Recycled Resin Content

Special Characteristics
High impact or impact modified

Regional Availability
Europe