

AZ564

PP

Sumitomo Chemical Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	30	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	24	MPa	ASTM D 638
Tensile Strength at Break	17	MPa	ASTM D 638
Flexural Modulus	1290	MPa	ASTM D 790
Rockwell Hardness	R 90	-	ASTM D 785
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 66 psi	109	°C	ASTM D 648
Vicat Temperature	151	°C	ASTM D 1525
Other properties			
Density	900	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Melt temperature	190 - 230	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Features

Nucleated, Copolymer, Impact Copolymer

Certifications

Food contact, Food approval 1935/2004/EC, Food approval 10/2011, Food approval FDA 21 CFR

Applications

Automotive, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific