

B1101

PP

SINOPEC Shanghai Gaoqiao Company

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards^[5]			
Melt flow index, MFI	0.3	g/10min	

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
Other Standards^[5]			
Yield stress	28.8	MPa	
Strain at break	>50	%	

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics**Features**

Copolymer

Regional Availability

Asia Pacific

Certifications

Food contact, Food approval FDA 21 CFR