

**B4901**

PP

SINOPEC Shanghai Gaoqiao Company

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Melt flow index, MFI	1.1	g/10min	

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Yield stress	29.6	MPa	
Flexural modulus, 23°C	1100	MPa	

S: These properties are reported by the producer according standards that are different to our defaults.

## Characteristics

### Features

Copolymer, Random Copolymer

### Regional Availability

Asia Pacific

### Applications

Medical