

B8101

PP

SINOPEC Shanghai Gaoqiao Company

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards^[5]			
Melt flow index, MFI	0.4	g/10min	

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
Other Standards^[5]			
Yield stress	23.5	MPa	
Strain at break	>50	%	

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Features

Copolymer

Regional Availability

Asia Pacific

Certifications

Food contact, Food approval FDA 21 CFR, Drinking water contact