

**Product Texts**

For a biaxially oriented film, a metallized film, products in contact with food, toys.

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	3	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

**Mechanical properties**

	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	32	MPa	ASTM D 638
Elongation at Yield	11	%	ASTM D 638
Flexural Modulus	1200	MPa	ASTM D 790

**Characteristics****Processing**

Film Extrusion

**Delivery form**

Pellets

**Certifications**

Food contact

**Applications**

Toys

**Regional Availability**

Europe, Asia Pacific