

BD950MO

PP

Borouge

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	1500	MPa	ISO 527
Yield stress	30	MPa	ISO 527
Yield strain	6	%	ISO 527
Flexural modulus, 23°C	1450	MPa	ISO 178
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Rockwell hardness	R 92	-	ISO 2039-2
ASTM Data			
Izod Impact notched, 1/8 in	85	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	50	J/m	ASTM D 256
Temperature	-20	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	100	°C	ISO 75-1/-2
Vicat softening temperature, A	149	°C	ISO 306
Other properties			
Density	905	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Melt temperature	210 - 260	°C	-
Mold temperature	10 - 30	°C	-
Holding pressure	20 - 50	MPa	-

Characteristics**Processing**

Injection Molding, Compression Molding

Special Characteristics

Anti-static, High impact or impact modified

Features

Blush Resistance/Low Crease Whitening, Creep Resistance, Melt Strength, Nucleated, Tribologic Grade, Copolymer

Certifications

Food contact, Food approval 1935/2004/EC, Food approval 10/2011, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa