

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.9	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	162	°C	ISO 11357-1/-3
Other properties			
Density	916	kg/m ³	ISO 1183

Characteristics

Processing

Coating

Features

Anti Slip, Thermal Stability

Delivery form

Powder, White

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa