

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	20	MPa	ISO 527
Strain at break	400	%	ISO 527
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Vicat softening temperature, A	145	°C	ISO 306
Other properties			
Density	900	kg/m ³	ISO 1183
Processing Recommendation Extrusion			
Melt temperature	250	°C	-
Nozzle temperature	210 - 240	°C	-

Characteristics

Processing

Other Extrusion, Coating

Delivery form

Pellets

Features

Good Adhesion, Thermal Stability

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa