

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	7.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	20	MPa	ISO 527
Strain at break	400	%	ISO 527
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Vicat softening temperature, A	145	°C	ISO 306
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Processing**

Other Extrusion, Coating

**Features**

Good Adhesion, Thermal Stability

**Delivery form**

Powder

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa