

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2.1	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	1400	MPa	ISO 527
Yield stress	20	MPa	ISO 527
Strain at break	400	%	ISO 527
Shore D hardness	65	-	ISO 7619-1
Thermal properties			
ISO Data			
Vicat softening temperature, A	140	°C	ISO 306
Other properties			
ISO Data			
Density	905	kg/m ³	ISO 1183
Processing Recommendation Extrusion			
ISO Data			
Melt temperature	225 - 235	°C	-
Zone 1	220 - 240	°C	-

Characteristics

Processing

Coating

Delivery form

Pellets

Features

Thermal Stability

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa