

Product Texts

This material contains 55% post-consumer recycled polymer.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	21	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1600	MPa	ISO 527
Charpy notched impact strength, +23°C	3.5	kJ/m ²	ISO 179/1eA

Characteristics**Certifications**

Recycled Resin Content

Regional Availability

Europe