

Product Texts

This material contains 55% post-consumer recycled polymer.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	22	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1500	MPa	ISO 527
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA

Characteristics**Special Characteristics**

High impact or impact modified

Regional Availability

Europe

Certifications

Recycled Resin Content