

**Bormod™ BJ368MO**

PP

Borouge

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>70</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>1500</b>	MPa	ISO 527
Yield stress	<b>25</b>	MPa	ISO 527
Yield strain	<b>4</b>	%	ISO 527
Flexural modulus, 23°C	<b>1500</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>5.5</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Rockwell hardness	<b>R 92</b>	-	ISO 2039-2
<b>ASTM Data</b>			
Izod Impact notched, 1/8 in	<b>55</b>	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	<b>40</b>	J/m	ASTM D 256
Temperature	<b>-20</b>	°C	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	<b>102</b>	°C	ISO 75-1/-2
Vicat softening temperature, A	<b>150</b>	°C	ISO 306
<b>Other properties</b>			
Density	<b>905</b>	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Melt temperature	<b>210 - 260</b>	°C	-
Mold temperature	<b>10 - 30</b>	°C	-
Holding pressure	<b>20 - 50</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Additives**

Release agent

**Special Characteristics**

Anti-static

**Features**

Nucleated, Copolymer

**Certifications**

Food contact, Food approval 1935/2004/EC, Food approval 10/2011, Food approval FDA 21 CFR

**Applications**

Packaging

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa