

**Capilene® SW 70 LE**

PP

Ducor Petrochemicals BV

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>65</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Flexural modulus, 23°C	<b>1200</b>	MPa	ISO 178
Izod notched impact strength, +23°C	<b>6.5</b>	kJ/m <sup>2</sup>	ISO 180/1A

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>900</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

High impact or impact modified

**Features**

Low Emission, Copolymer

**Applications**

Automotive

**Regional Availability**

Europe, Asia Pacific, Near East/Africa