

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	55	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	38.6	MPa	ASTM D 638
Elongation at Yield	6.5	%	ASTM D 638
Izod Impact notched, 1/8 in	27	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	120	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Certifications

Food contact

Special Characteristics

Anti-static

Applications

Packaging

Features

Nucleated, Homopolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa