

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	20	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	19.6	MPa	ASTM D 638
Elongation at Yield	9.5	%	ASTM D 638
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	92	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m³	ASTM D 792

**Characteristics**

**Special Characteristics**

Anti-static, High impact or impact modified

**Features**

Nucleated, Copolymer, Impact Copolymer

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa