

CP 295

PP

Braskem

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
ASTM Data			
Melt Flow Index, MFI	20	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	650	MPa	ISO 178
Izod notched impact strength, +23°C	49	kJ/m ²	ISO 180/1A
Izod notched impact strength	8.2	kJ/m ²	ISO 180/1A
Temperature	-20	°C	-
Rockwell hardness	R 34	-	ISO 2039-2
ASTM Data			
Tensile Strength at Yield	18	MPa	ASTM D 638
Elongation at Yield	6	%	ASTM D 638
Rockwell Hardness	R 46	-	ASTM D 785
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	100	J/m	ASTM D 256
Temperature	-20	°C	-
Other properties			
Density	895	kg/m ³	ISO 1183
Density	895	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Features

Copolymer

Special Characteristics

High impact or impact modified

Regional Availability

North America, Europe, South and Central America