

**CP PRYME® Polypropylene PPC300/2I-20M**

PP

Chase Plastics

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>20</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	<b>23.4</b>	MPa	ASTM D 638
Flexural Modulus	<b>1140</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>110</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>82.2</b>	°C	ASTM D 648
<b>Other properties</b>			
Density	<b>908</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Delivery form**

Pellets

**Certifications**

Recycled Resin Content

**Features**

Copolymer

**Regional Availability**

North America