

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	14960	MPa	ISO 527
^[C] Stress at break	49	MPa	ISO 527
^[C] Strain at break	0.35	%	ISO 527
^[C] Charpy impact strength, +23°C	3.5	kJ/m ²	ISO 179/1eU

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1610	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Special Characteristics

Increased electrical conductivity, Thermally Conductive

Features

EMI Attenuation/Shielding