

Nemcon™ H PPS DP148

PPS

Ovation Polymers

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Modulus | 4500 | MPa | ASTM D 638 |
| Tensile Strength at Break | 53 | MPa | ASTM D 638 |
| Elongation at Break | 2.1 | % | ASTM D 638 |
| Flexural Modulus | 4700 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 26.7 | J/m | ASTM D 256 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1890 | kg/m ³ | ASTM D 792 |

Characteristics**Regional Availability**

North America