

Nemcon™ H PPS Dp183

PPS

Ovation Polymers

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	8515	MPa	ASTM D 638
Tensile Strength at Break	110	MPa	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	9915	MPa	ASTM D 790
Izod Impact notched, 1/8 in	78.5	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1720	kg/m ³	ASTM D 792

Characteristics

Regional Availability

North America