

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	12070	MPa	ASTM D 638
Tensile Strength	44.8	MPa	ASTM D 638
Flexural Modulus	12070	MPa	ASTM D 790
Flexural Strength	72.4	MPa	ASTM D 790
Izod Impact notched, 1/8 in	26.7	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.59	mm	-

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	10000	Ohm	ASTM D 257
Volume Resistivity	100	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1630	kg/m ³	ASTM D 792
Moisture Content	0.04	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	149	°C	-
Pre-drying - Time	6	h	-
Melt temperature	307 - 329	°C	-
Mold temperature	135 - 177	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Increased electrical conductivity