

**Ryton® QA200P**

PPS

Syensqo

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	100	g/10min	ASTM D 1238
Temperature	316	°C	-
Load	5	kg	-
Mold Shrinkage, MD	0.01	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	3400	MPa	ISO 527
Tensile Strength	80	MPa	ISO 527
Strain at break	4	%	ISO 527
Flexural modulus, 23°C	3400	MPa	ISO 178
Izod notched impact strength, +23°C	4	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Izod Impact notched, 1/8 in	53	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	280	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	90	°C	ISO 11357-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
<b>ASTM Data</b>			
DTUL @ 66 psi	160	°C	ASTM D 648
DTUL @ 264 psi	95	°C	ASTM D 648
Limiting Oxygen Index	44	%	ASTM D 2863

Electrical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Dielectric Strength, Short Time	24	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.002	-	ASTM D 150
Dielectric Constant, 1 MHz	3.2	-	ASTM D 150
Surface Resistivity	>1E15	Ohm	ASTM D 257
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.05	%	ASTM D 570
Density	1340	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Features**

Thermal Stability

**Chemical Resistance**

General Chemical Resistance

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa