

**AQUALOY® TR314-2**

PPS-GF

LyondellBasell Industries

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Flexural modulus, 23°C	<b>15000</b>	MPa	ISO 178
Izod notched impact strength, +23°C	<b>3.3</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>250</b>	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	<b>1840</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Regional Availability**

North America, Europe, Asia Pacific, South and Central America,  
Near East/Africa