

Product Texts

LNP LUBRICOMP DFL24 compound is based on Polycarbonate (PC) resin containing 20% glass fiber, 10% PTFE. Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E45329-101344594](https://www.ul.com/yellow-card/E45329-101344594)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.4	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.6	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	5610	MPa	ISO 527
Yield stress	86	MPa	ISO 527
Yield strain	3	%	ISO 527
Stress at break	92	MPa	ISO 527
Strain at break	3.3	%	ISO 527
Flexural modulus	5800	MPa	ISO 178
Flexural strength	136	MPa	ISO 178
Izod impact strength, +23°C, 4mm	50	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	15	kJ/m ²	ISO 180/1A

ASTM Data			
Tensile Modulus	5700	MPa	ASTM D 638
Tensile Strength at Yield	87	MPa	ASTM D 638
Tensile Strength at Break	86	MPa	ASTM D 638
Elongation at Yield	3.2	%	ASTM D 638
Elongation at Break	3.6	%	ASTM D 638
Flexural Modulus	5500	MPa	ASTM D 790
Izod Impact notched, 1/8 in	152	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	715	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	143	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	146	°C	ISO 75-1/-2
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
ASTM Data			
Coefficient of Thermal Expansion, MD	37.1	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	52.9	E-6/K	ASTM D 696
DTUL @ 66 psi	147	°C	ASTM D 648
DTUL @ 264 psi	143	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Humidity absorption	0.13	%	Sim. to ISO 62
Water Absorption, 24hr	0.08	%	ASTM D 570
Density	1410	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	305 - 325	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	295 - 305	°C	-
Zone 2	310 - 320	°C	-
Zone 3	320 - 330	°C	-
Screw speed	30 - 60	rpm	-

Back pressure	0.2 - 0.3	MPa	-
---------------	------------------	-----	---

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific