

Ryton® R-4-02XT

PPS-GF40

Syensqo

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.005	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	180	MPa	ISO 527
Strain at break	1.4	%	ISO 527
Flexural modulus, 23°C	14000	MPa	ISO 178
Izod impact strength, +23°C	30	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	8	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Strength	179	MPa	ASTM D 638
Elongation at Break	1.5	%	ASTM D 638
Compressive Strength	285	MPa	ASTM D 695
Flexural Modulus	14500	MPa	ASTM D 790
Flexural Strength	255	MPa	ASTM D 790
Rockwell Hardness	M 102	-	ASTM D 785
Izod Impact notched, 1/8 in	80	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	350	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at 1.5 mm nom. thickn. Thickness tested	V-0	class	IEC 60695-11-10
Burning behav. 5V at thickness h Thickness tested	1.6	mm	-
Burning behav. 5V at thickness h Thickness tested	5VA	class	IEC 60695-11-20
Burning behav. 5V at thickness h Thickness tested	1.6	mm	-
ASTM Data			
DTUL @ 264 psi	265	°C	ASTM D 648
Limiting Oxygen Index	53	%	ASTM D 2863

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Dielectric Strength, Short Time	22	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.003	-	ASTM D 150
Dielectric Constant, 1 MHz	3.9	-	ASTM D 150
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Arc Resistance	125	s	ASTM D 495

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.02	%	ASTM D 570
Density	1690	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Chemical Resistance

General Chemical Resistance

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa