

**Product Texts**

LNP LUBRICOMP DFP34 compound is based on Polycarbonate (PC) resin containing 20% glass fiber, 15% PTFE/silicone. Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E45329-101344453](https://www.ulprospector.com/usa/Products/Plastics/PC-PTFE-GF20-101344453)

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>6200</b>	MPa	ISO 527
Stress at break	<b>89</b>	MPa	ISO 527
Strain at break	<b>2.6</b>	%	ISO 527
Izod notched impact strength, +23°C, 4mm	<b>11</b>	kJ/m <sup>2</sup>	ISO 180/1A

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>140</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>145</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	<b>34</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	<b>62</b>	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	<b>V-1</b>	class	IEC 60695-11-10
Thickness tested	<b>3.0</b>	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1420</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Processing**

Injection Molding

**Regional Availability**

Europe