

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.5	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	13300	MPa	ISO 527
^[C] Stress at break	180	MPa	ISO 527
^[C] Strain at break	2.4	%	ISO 527
^[C] Charpy impact strength, +23°C	60	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	65	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	13	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	12	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	280	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	90	°C	ISO 11357-1/-2
^[C] Temp. of deflection under load, 1.80 MPa	266	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	279	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	263	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	15	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	48	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Yellow Card available	yes	-	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	33	kV/mm	IEC 60243-1
^[C] Comparative tracking index	175	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1600	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing Injection Molding	Special Characteristics High impact or impact modified
--	--

Delivery form Granules	Regional Availability North America, Europe, Asia Pacific
----------------------------------	---

Other text information

Injection molding

[Injection Molding Recommendations](#)
[Hot runner recommendations for molding high heat performance Engineering Materials](#)
[Recommendations for machining Xytron](#)