

Product Texts

According with the requirements of Standard ISO 14021:2016, CirculenRecover PPMI20 Jazz contains at least 99 % of recycled material that is fully based on Post-Consumer Waste (PCW) from pre-sorted municipal plastic waste. Filtration level is 150 µm.
 Melt Flow Rate, (230 °C/2.16 kg): 14-25 g/10 min

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	19	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Other properties	Value	Unit	Test Standard
Density	915	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

High impact or impact modified

Features

Copolymer, Impact Copolymer

Certifications

Recycled Resin Content

Applications

General Purpose, Packaging

Regional Availability

Europe