

Product Texts

LNP LUBRICOMP DFL16E compound is based on Polycarbonate (PC) resin containing 30% glass fiber and 5% PTFE. Added features of this grade include: Wear Resistant, Easy Molding.

UL Yellow Card Link [E207780-101344587](https://www.ulprospector.com/usa/Products/Plastics/PC+PTFE-GF30)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.3	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	8810	MPa	ASTM D 638
Tensile Strength at Break	100	MPa	ASTM D 638
Elongation at Break	2	%	ASTM D 638
Flexural Modulus	7920	MPa	ASTM D 790
Flexural Strength	151	MPa	ASTM D 790
Izod Impact notched, 1/8 in	90	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	655	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
ASTM Data			
DTUL @ 264 psi	140	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1500	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	305 - 325	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	295 - 305	°C	-
Zone 2	310 - 320	°C	-
Zone 3	320 - 330	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics

Processing
Injection Molding

Regional Availability
North America, Europe, Asia Pacific