

Clyrell RC112G

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1.7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	130	°C	ISO 11357-1/-3
Vicat softening temperature, A	113	°C	ISO 306
Optical properties			
ASTM Data			
Gloss	90	-	ASTM D 2457
Haze	0.5	%	ASTM D 1003
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Blown Film Extrusion, Film Extrusion

Applications

Packaging

Features

Copolymer, Random Copolymer

Regional Availability

Europe

Certifications

Food contact