

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	55	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	24.2	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Flexural Modulus	1207	MPa	ASTM D 790
Izod Impact notched, 1/8 in	66.7	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 264 psi	108	°C	ASTM D 648
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Special Characteristics

High impact or impact modified

#### Features

Copolymer, Impact Copolymer

#### Certifications

Food contact, Food approval FDA 21 CFR

#### Regional Availability

North America