

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	11	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	17	MPa	ISO 527
Flexural modulus, 23°C	850	MPa	ISO 178
Charpy notched impact strength, +23°C	60	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	7.5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	71	°C	ISO 75-1/-2
Other properties			
Density	900	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2	h	-
Melt temperature	220 - 260	°C	-
Mold temperature	30 - 50	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa