

**Daploy™ WB140HMS**

PP

Borealis A/S

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>2.1</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>2000</b>	MPa	ISO 527

**Characteristics****Processing**

Other Extrusion

**Features**

Acoustical Barrier Properties, Foamable, Thermal Stability, Homopolymer

**Certifications**

Food contact

**Applications**

Automotive, Packaging

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa