

**DP 105A**

PP

Braskem

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>40</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>39</b>	MPa	ASTM D 638
Elongation at Yield	<b>9</b>	%	ASTM D 638
Rockwell Hardness	<b>R 100</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>27</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>117</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>65</b>	°C	ASTM D 648
Vicat Temperature	<b>154</b>	°C	ASTM D 1525
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	<b>24</b>	%	ASTM D 1003
<b>Other properties</b>			
Density	<b>905</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Transparent

**Features**

Homopolymer

**Certifications**

Food contact

**Applications**

Packaging

**Regional Availability**

North America, Europe, South and Central America