

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	48	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	1900	MPa	ISO 527
Yield stress	39	MPa	ISO 527
Yield strain	7	%	ISO 527
Strain at break	20	%	ISO 527
Charpy impact strength, +23°C	75	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	11	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	2	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	1	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	2.2	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	1.1	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-
Ball indentation hardness	90	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	163	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	100	°C	ISO 75-1/-2
Vicat softening temperature, A	155	°C	ISO 306
Vicat softening temperature, B	98	°C	ISO 306

Optical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Haze	11	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	910	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Delivery form**

Pellets

**Special Characteristics**

Anti-static, Transparent

**Features**

Low Odor, Nucleated, Homopolymer

**Certifications**

Food contact, Food approval 1935/2004/EC, Food approval FDA 21 CFR

**Applications**

Packaging

**Regional Availability**

Europe, Asia Pacific, Near East/Africa