

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	1500	MPa	ISO 527
Charpy notched impact strength, +23°C	3.5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	163	°C	ISO 11357-1/-3
Vicat softening temperature, A	154	°C	ISO 306
Vicat softening temperature, B	90	°C	ISO 306
Other properties			
Density	910	kg/m ³	ISO 1183

Characteristics

Processing

Film Extrusion, Thermoforming

Additives

Antiblocking agent

Special Characteristics

Anti-static

Regional Availability

Europe, Asia Pacific, Near East/Africa