

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	1600	MPa	ISO 527
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	163	°C	ISO 11357-1/-3
Other properties			
Density	910	kg/m ³	ISO 1183

Characteristics

Regional Availability

Europe, Asia Pacific, Near East/Africa